

DELTA-PROTEKT® VH 390 SCHW

Article number: 08405511

DELTA-PROTEKT® VH 390 SCHW is a topcoat for an electroplated substrates. In the system zinc + topcoat it is responsible for multifunctional characteristics such as a defined coefficient of friction window, resistance to media, colouring etc. The DELTA-PROTEKT® VH 390 SCHW is applied via a non-electrolytic application technique directly onto the substrate (part). The zinc flake technique is described in the standards DIN EN ISO 10683 and DIN EN ISO 13858. The application technology can vary according to the dimension and weight of the part; e.g. small parts are usually coated as dip-spin, bigger parts are usually spray coated. All Dörken MKS products have always been free of harmful heavy metals such as chromium VI. As there is no hydrogen involved during the application process, there is no danger of application-related hydrogen-induced stress corrosion cracking.

CATEGORY



VH-Topcoat



REQUIREMENTS

Corrosion resistance

• enhances the corrosion protection of the basecoat

Special features

- hybrid system
- water-based

Media resistance

• fulfils chemical resistance against operating fluids according to DIN EN ISO 2812


Resistance against

- Corrosion resistance
- Media resistance

Surface / Substrate

- zinc flake basecoat
- passivated zinc/zinc alloys
- extreme thin layers of 1-3 μm possible
- Even layer construction possible.
- The technical feasibility depends on pretreatment and individual characteristics of each material.

Application technology



dip-spin spray

Legal conditions

• meets the EU End-of-Life Vehicle Directive 2000/53/EC




- meets the RoHS 2 guidelines (also known as EU Directive on the Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment 2002/95/EC)
- meets the REACh requirements

Contact Person

• Emre Kocak

SELECTION OF SUITABLE PARTS

Advised parts



Pipes and tubes

Brake parts



Suitable parts



Metrical threaded bolts M2-M16

SPECIFICATIONS

ASTM - F3393

ISO - ISO/EN 10683

ASTM - F3125